

DECLARATION OF PERFORMANCE

No. 10/2021

1. Unique identification code of the product-type:

Gränges_Konin_3103_RYF

2. Intended use or uses:

Intended for internal and external loaded construction elements of buildings.

3. Manufacturer:

Gränges Konin S.A., Bolesława Prusa 2 Street, 00-493 Warsaw, Poland
Correspondence address: Hutnicza 1 Street, 62-510 Konin, Poland

4. System or systems of assessment and verification of constancy of performance:

System 2+

5. Harmonized standard:

EN 15088: 2005

Notified body/ies:

Research and Certification Department „ZETOM” prof. F. Stauba in Katowice sp. z o.o.,
Notified Body number 1436

6. Declared performance: Sheet and strip ribbed aluminium alloy EN AW-3103

Essential characteristics	Performance	Harmonized technical specification																	
Tolerances on dimensions and shape PN-EN 1386	Thickness tolerances	PN-EN 15088:2005																	
	<table border="1"> <thead> <tr> <th colspan="2">Nominal thickness „t” [mm]</th> <th>The maximum thickness tolerance for specified width [mm]</th> </tr> <tr> <th colspan="2"></th> <th>Up to and including 1600mm</th> </tr> </thead> <tbody> <tr> <td>≥1,2</td> <td>2,5</td> <td>±0,20</td> </tr> <tr> <td>>2,5</td> <td>3,5</td> <td>±0,30</td> </tr> <tr> <td>>3,5</td> <td>5,0</td> <td>±0,40</td> </tr> </tbody> </table>		Nominal thickness „t” [mm]		The maximum thickness tolerance for specified width [mm]			Up to and including 1600mm	≥1,2	2,5	±0,20	>2,5	3,5	±0,30	>3,5	5,0	±0,40		
	Nominal thickness „t” [mm]		The maximum thickness tolerance for specified width [mm]																
			Up to and including 1600mm																
	≥1,2		2,5	±0,20															
	>2,5		3,5	±0,30															
	>3,5		5,0	±0,40															
	Width tolerances for sheet and strip																		
	<table border="1"> <thead> <tr> <th rowspan="2">Nominal thickness „t” [mm]</th> <th colspan="2">Width tolerance for specified width [mm]</th> </tr> <tr> <th>Up to and including 1500mm</th> <th>Over 1500mm up to and including 2500mm</th> </tr> </thead> <tbody> <tr> <td>1,2≤t≤3,0</td> <td>+1,5 0</td> <td>+8 0</td> </tr> <tr> <td>3,0≤t≤8,0</td> <td>+3 0</td> <td>+10 0</td> </tr> <tr> <td>t>8,0</td> <td>+5 0</td> <td>+8 0</td> </tr> </tbody> </table>		Nominal thickness „t” [mm]	Width tolerance for specified width [mm]		Up to and including 1500mm	Over 1500mm up to and including 2500mm	1,2≤t≤3,0	+1,5 0	+8 0	3,0≤t≤8,0	+3 0	+10 0	t>8,0	+5 0	+8 0			
	Nominal thickness „t” [mm]			Width tolerance for specified width [mm]															
Up to and including 1500mm		Over 1500mm up to and including 2500mm																	
1,2≤t≤3,0	+1,5 0	+8 0																	
3,0≤t≤8,0	+3 0	+10 0																	
t>8,0	+5 0	+8 0																	
Length tolerances for sheet																			
<table border="1"> <thead> <tr> <th rowspan="2">Nominal thickness „t” [mm]</th> <th colspan="3">Length tolerance for specified length [mm]</th> </tr> <tr> <th>Up to and including 2000mm</th> <th>Over 2000mm up to and including 5000mm</th> <th>Over 5000mm</th> </tr> </thead> <tbody> <tr> <td>1,2≤t≤3,0</td> <td>+8 0</td> <td>+10 0</td> <td>+12 0</td> </tr> <tr> <td>3,0≤t≤8,0</td> <td>+8 0</td> <td>+10 0</td> <td>+12 0</td> </tr> <tr> <td>t>8,0</td> <td>+6 0</td> <td>+8 0</td> <td>+10 0</td> </tr> </tbody> </table>	Nominal thickness „t” [mm]	Length tolerance for specified length [mm]			Up to and including 2000mm	Over 2000mm up to and including 5000mm	Over 5000mm	1,2≤t≤3,0	+8 0	+10 0	+12 0	3,0≤t≤8,0	+8 0	+10 0	+12 0	t>8,0	+6 0	+8 0	+10 0
Nominal thickness „t” [mm]		Length tolerance for specified length [mm]																	
	Up to and including 2000mm	Over 2000mm up to and including 5000mm	Over 5000mm																
1,2≤t≤3,0	+8 0	+10 0	+12 0																
3,0≤t≤8,0	+8 0	+10 0	+12 0																
t>8,0	+6 0	+8 0	+10 0																

Essential characteristics	Performance										Harmonized technical specification
Mechanical properties PN-EN 1386	Temper	Specified thickness		Tensile strength R _m		Yield strength R _{p0,2}		Elongation A50 mm		Bend radius	PN-EN 15088:2005
		[mm]		[MPa]		[MPa]		[%]			
	Over	Up to and including	min	max	min	max	min	max	90°		
	H224	1,2	1,5	115	175	75		3		1,25t	
		1,5	3,0	115	175	75		4		1,5t	
3,0		6,0	115	175	75		5		2,5t		
6,0		20,0	115	175	75		6	10	-		
H244	1,2	1,5	140	195	110		2		1,25t		
	1,5	3,0	140	195	110		3		1,5t		
	3,0	6,0	140	195	110		4		2,5t		
	6,0	20,0	140	195	110		5	7	-		
Weldability PN-EN 1999-1-1	Class I										
Bendability	Alloy	Temper									
		H224					H244				
	EN AW-3103	-					-				
Fatigue strength	NPD										
Dangerous substances PN-EN 573-3	NO										
Durability rating PN-EN 1999-1-1	Class A										

The performance of the product identified above is in conformity with the declared performance/s.
This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011,
under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

Paweł Rutecki
Director of Development and Investment

Konin, 13 April 2021

Director of Development & Investment



Paweł Rutecki